



BonuCel® – the flexible polymer for your formulation needs:





BonuCel® provides easy-to-use cellulose ethers for pharmaceutical and nutritional products. The main application of Hypromellose is film coating. The fine, homogeneous blends of selected high quality cellulose ether polymers provide excellent film forming properties and sustained release profiles. A wide range of standard viscosities is offered to deal with different application requirements. Additionally, BIOGRUND offers an exclusive service by finely adjusting viscosities.

Film coating with hydroxypropylmethylcellulose is a well known, established and effective technique. These coatings are now in widespread use throughout the world. BonuCel® does not interact with drugs, and it has a superior stability and non-ionic character, so it is also effective as a binder. Due to its more stable characteristics, BonuCel® can also be used instead of gelatine for cellulose capsule manufacturing.

The high-viscosity BonuCel®-types are exclusively designed for a hydrophilic matrix agent. This is the easiest sustained release technology for oral dosage forms, consisting essentially of a drug and a water-soluble high viscous polymer.

BonuCel® is produced in accordance with IPEC GMP guidelines and meets all requirements of USP/NF, Ph.Eur. and JP.

BonuCel® consists of highly purified cellulose fibres based on natural raw materials. Mainly renewable wood fibres are used as the primary raw material for the production of cellulose ethers.

DESCRIPTION

Trade name	BonuCel®
Generic name	Hypromellose
	(Hydroxypropyl-
	methylcellulose)
Abbreviation	НРМС
Chemical name	Cellulose,
	2-hydroxypropyl
	methyl ether
CAS registry number	9004-65-3
Compendial status	USP / EP / JP

STRUCTURAL FORMULA

$$\begin{bmatrix} OR & CH_2OR \\ OR & OR \\ CH_2OR & OR \\ \end{bmatrix}$$

$$R = -H$$

$$-CH_3$$

$$-CH_2CH (CH_3)OH$$

TYPICAL POLYMER PROPERTIES

film/gel forming, water-/organo-soluble, high swelling, viscosifying, non-caloric, hydrophilic, mucoadhesive

How to dissolve pure BonuCel® H for a HPMC Solution

Ν	WAT	ER
(A)		

Heat 1/3 of the total amount of water needed to above 70°C.

Quickly add all of the BonuCel® H to hot water while stirring well.

Add the remaining cold water (5 °C) to make the prescribed volume while stirring well.

Stir the solution for an additional 30 minutes, or until the solution is lump free.

If a high-power stirrer is used, BonuCel® H can be directly dissolved by adding it gradually to the water at below 30 °C with stirring. Care must be taken to avoid bubble or foam formation.

IN ORGANIC SOLVENTS (B)

Pour a prescribed volume of ethanol into a container and put all of the BonuCel® H in it while stirring.


When a uniform dispersion is obtained, add methylene chloride gradually and stir gently to form a well-wetted dispersion as the coating solution.

TIPS

If BonuCel® H is added all at once into a previously prepared mixed solution, insoluble lumps will be formed.

If difficulties arise concerning the dissolution apparatus, removal of bubbles in the coating solution or filtration of solutions, BIOGRUND can offer technical advice based on extensive experience and know-how.

Great care should be taken to avoid any foreign material contamination. However, we recommend sieving the product and/or filtering the product solution before usage.



Nomenclature

BonuCel® D 6 H 2910 Tradename of BIOGRUND Quality: P = Pharma F = Food Cellulose type: H = Hypromellose Chemistry: Substitution type

Specifications

			_		
Standard Grades	Viscosities (mPa·s)	Methoxy Content	Hydroxypropoxy Content	Typical Application	Function
BonuCel® D 3 H 2910 Product Code: 101184	2.4-3.6	28.0-30.0 %	7.0-12.0 %	Film coating / Wet granulation	Film / Binder
BonuCel® D 5 H 2910 Product Code: 102072	4.0-6.0	28.0-30.0 %	7.0-12.0 %	Film coating	Film
BonuCel® D 6 H 2910 Product Code: 102021	4.8-7.2	28.0-30.0 %	7.0-12.0 %	Film coating	Film
BonuCel® D 15 H 2910 Product Code: 102027	12.0-18.0	28.0-30.0 %	7.0-12.0 %	Film coating	Film
BonuCel® D 50 H 2910 Product Code: 102020	40.0-60.0	28.0-30.0 %	7.0-12.0 %	Film coating / Suspensions	Film / Thickener
BonuCel® D 100 H 2208 Product Code: 102107	80-120	19.0-24.0 %	4.0-12.0 %	Thickening agent / Sustained releas	Thickener / Matrix
BonuCel® D 4000 H 2910 Product Code: 102032	3000-5600	28.0-30.0 %	7.0-12.0 %	Thickening agent	Thickener
BonuCel® D 4000 H 2906 Product Code: 103005	3000-5600	27.0-30.0 %	4.0-7.5 %	Thickening agent	Thickener
BonuCel® D 4000 H 2208 Product Code: 102037	3000-5600	19.0-24.0 %	4.0-12.0 %	Thickening agent / Sustained release	Thickener / Matrix
BonuCel® D 15000 H 2208 Product Code: 102106	11250-21000	19.0-24.0 %	4.0-12.0 %	Thickening agent / Sustained release	Thickener / Matrix
BonuCel® D 100000 H 2208 Product Code: 102079	75000-140000	19.0-24.0 %	4.0-12.0 %	Thickening agent / Sustained release	Thickener / Matrix

Application

Example of coating parameters for an aqueous solution (production scale)


COMPOSITION OF COATING SOL ITION

BonuCel® D 6 H 2910	6 % BonuCel® / 94 % water

COATING CONDITIONS

Apparatus	New Hi-Coater HC-130N (Freund corporation)
Dimension	1300 mm
Pan speed	8 min ⁻¹
Spray gun	Air spray gun X3 (AT type nozzle diameter 1.2 mm)
Drying air	80°C
Air flow rate	15 m³/min
Spray speed	70 g/min x3
Nozzle air	170 L/min
Nozzle air + pattern air	250 L/min
Tablet bed temperature	46°C
Charge per batch	120 kg
Dosage form	6.5 mm, 120 mg/Tablet

Coating Process



- 1 Blower (Air in
- 2 Solution/Dispersion with Pump
- 3 Spray Gun
- 4 Tablet Bed
- 5 Blower (Air out)

Specifications valid for all BonuCel® H (Hypromellose) Types

Appearance	white to slightly off-white powder	
Solubility	Practically insoluble in hot water, in acetone, in anhydrous ethanol and toluene. It dissolves in cold water giving a colloidal solution.	PhEur
Identity A, B, C, D, E	passed	USP/PhEur
Appearance of solution	passed	PhEur
Organic volatile impurities	passed	USP
Loss on drying	<5%	USP/PhEur
pH value	5.0-8.0	USP/PhEur
Sulphated ash	<1.5%	USP/PhEur
Heavy metals	<20 ppm	USP
Standard plate count	<10³ cfu/g	USP/PhEur
Yeast and mold	<10² cfu/g	USP/PhEur
Coliforms	abs/g	USP/PhEur
Samonella	abs/10g	USP/PhEur

REGULATORY AND QUALITY ASPECTS

All BonuCel®-types can be used for pharmaceutical products and for nutritional or dietary supplements.

Product Safety

BIOGRUND encourages and expects you to read and understand the entire Material Safety Data Sheet, as it contains important information – especially the first-aid, fire-fighting and toxical information.

HAZARDS IDENTIFICATION	Classification of the substance/preparation: This product is not classified as dangerous, according to EC criteria.
PERSONAL PROTECTION	Protective gloves are needed when handling this material. Consistent with general hygienic practice for any material, skin contact should be minimized.
	Use safety glasses. Safety glasses should be consistent with EN 166 or equivalent.
	Wash hands before smoking or eating.
HANDLING AND STORAGE	Good housekeeping with respect to dust is necessary for safe handling of product. Avoid dust formation. Provide exhaust ventilation if dust forms.
	Keep away from heat, sparks and flame. No smoking open flames or sources of ignition in handling and storage area.
	Store in a dry and cool place. Keep container well closed.
DISPOSAL	Any disposal practice must be in compliance with all local and national laws and regulations. Do not dump into any sewers or on the ground or in the water.
	According to local regulations, empty drums or containers can be washed out for recycling. Do not allow washing water to enter inter watercourses.
	Packing must be recycled in accordance with national and local regulations for environmental protection.

General Information on BIOGRUND

Since 1999, **BIOGRUND** has been the specialist for the homogeneous mixing of excipients and carriers. With locations in Germany, Switzerland, America and Russia, we support the food supplement and pharmaceutical industry in the development, formulation and production of solid oral dosage forms. The tailor-made and ready-to-use special powder mixtures for film coating, sugarcoating, coloring and tableting enable optimum results in a short time. Easy, fast and reliable!

Locations

EUROPE

Germany

T +49 (0) 6126-952 63-0

Switzerland

T +41 (0) 41-747 14-50

USA

T +1 (502) 901-2980

RUSSIA

T +7 (495) 116-0386

Global contact:

www.biogrund.com/contact

Visit our website

www.biogrund.com

Follow us on:

in LinkedIn



Instagram

